

2007 Clear Scratch Resistant (normal hardeners)

Product description

2 pack High Solids Compliant Clear. High functionality at low viscosity.

Products

2007 with 4960 Standard

2007 with 4965 Fast

2007 with 4970 Extra Fast

Note

Product should be at 20°C prior to use.

Information contained herein is based on careful investigation and is intended for information only. User is obliged to test the suitability of the products for their particular use. Supplier may change any specifications without notice.

Uses

Panel repairs


Resprays

The EU limit value for this product (product category IIB.e) in ready for use form is max. 840 g/litre of VOC. The VOC content of this product in ready for use form is 600 g/l – 2004/42/IIB.e (840) 600

Composition	Acrylic resins, solvents
Colour	Water clear
Shelf life	Lacquer 36 months / Hardener 9 months
Pack Size	5 litre Clear/2½ litre hardener, 1 litre Clear/500ml hardener

Pre-treatment

2007 Clear Scratch Resistant can be applied to solvent and waterborne basecoats.

	<h3><u>Health and Safety</u></h3> <p>"For professional use only" Important: When using any new product, consult the "Health and Safety" data sheet. Always read the risks and precautions stated on the product label.</p>											
	<h3><u>Mix Ratio</u></h3> <table border="1"><thead><tr><th>2:1 (stir well and strain before application)</th><th>Volume</th><th>Weight</th></tr></thead><tbody><tr><td>2 parts Diamond Clear</td><td rowspan="2">2:1</td><td>100g</td></tr><tr><td>1 part Hardener</td><td>55g</td></tr><tr><td>600 – Universal thinner optional</td><td>Up to 10%</td><td></td></tr></tbody></table>	2:1 (stir well and strain before application)	Volume	Weight	2 parts Diamond Clear	2:1	100g	1 part Hardener	55g	600 – Universal thinner optional	Up to 10%	
2:1 (stir well and strain before application)	Volume	Weight										
2 parts Diamond Clear	2:1	100g										
1 part Hardener		55g										
600 – Universal thinner optional	Up to 10%											

	<p>Spraying viscosity 18 – 20 seconds BS4 cup at 20°C 14 seconds DIN4 cup at 20°C</p> <p>Pot life 2 - 2½ hours at 20°C</p>												
	<p>Application Product and air need to be at ambient 20°C</p> <table border="1" data-bbox="493 579 1389 878"><thead><tr><th data-bbox="493 579 970 631">Spray Gun</th><th data-bbox="970 579 1129 631">Fluid tip size</th><th data-bbox="1129 579 1389 631">Working pressure</th></tr></thead><tbody><tr><td data-bbox="493 631 970 698">LVLP Compliant Gravity-feed spray gun</td><td data-bbox="970 631 1129 698">1.3 to 1.4mm</td><td data-bbox="1129 631 1389 698">2 – 2.5 bar</td></tr><tr><td data-bbox="493 698 970 765">Divilbiss GTI Air cap 110</td><td data-bbox="970 698 1129 765">1.3mm</td><td data-bbox="1129 698 1389 765">2 – 2.5 bar</td></tr><tr><td data-bbox="493 765 970 878">HVLP gravity-feed</td><td data-bbox="970 765 1129 878">1.3 – 1.4mm</td><td data-bbox="1129 765 1389 878">0.7 bar at nozzle</td></tr></tbody></table> <p>1st coat: half coat 2nd coat: full wet coat 3rd coat: optional Flash off: 5-8 minutes Film thickness : 40 – 50 microns</p>	Spray Gun	Fluid tip size	Working pressure	LVLP Compliant Gravity-feed spray gun	1.3 to 1.4mm	2 – 2.5 bar	Divilbiss GTI Air cap 110	1.3mm	2 – 2.5 bar	HVLP gravity-feed	1.3 – 1.4mm	0.7 bar at nozzle
Spray Gun	Fluid tip size	Working pressure											
LVLP Compliant Gravity-feed spray gun	1.3 to 1.4mm	2 – 2.5 bar											
Divilbiss GTI Air cap 110	1.3mm	2 – 2.5 bar											
HVLP gravity-feed	1.3 – 1.4mm	0.7 bar at nozzle											
	<p>Drying All force dry/infrared times operate @ 60°C Metal 80°C Air</p> <p>4960 – 35 minutes force dry or 18 - 24 hours air dry @ 20°C 4965 – 20 minutes force dry or 12 - 18 hours air dry @ 20°C 4970 – 15 minutes force dry or 6 - 12 hours air dry @ 20°C</p>												